



DISSIPATIVE PINK POLY



Specifications:

Electrical Properties

Static Decay
 Surface Resistance
 Polycarbonate Haze
 Corrosivity Observations

Typical Values

<1.0 sec.
 < 10¹¹ Ohms
 NE
 NE

Test Procedures/Method

ASTM 101 Method 4046
 ESD S11.11
 72 hr contact
 MIL-STD-3010, M3005

Physical Properties


Thickness
 Melt Index
 Density
 Dart Impact
 Coefficient of Friction
 1% Secant Modulus (Stiffness)

4 mils
 0.050 gm/10 min
 0.923 gm/cc
 230 gms
 MD 24,000 psi
 MD 25,000 psi

ASTM D-1238
 ASTM D-1505
 ASTM D-1709
 ASTM D-1894 (unmodified film)
 ASTM D-882

| Item No. | Size (in.) W x L | Item No. | Size (in.) W x L |
|----------|---------------------|----------|---------------------|
| 49100 | 2 x 3 | 49110 | 8 x 12 |
| 49101 | 3 x 4 | 49111 | 10 x 12 |
| 49102 | 3 x 5 | 49112 | 10 x 14 |
| 49103 | 4 x 6 | 49113 | 10 x 20 |
| 49104 | 5 x 7 | 49114 | 12 x 16 |
| 49105 | 5 x 8 | 49115 | 14 x 16 |
| 49106 | 6 x 8 | 49116 | 15 x 18 |
| 49107 | 6 x 9 | 49117 | 16 x 20 |
| 49108 | 6 x 10 | 49118 | 18 x 20 |
| 49109 | 8 x 10 | 49119 | 18 x 24 |

Packaged 100 per package



Made in America

RoHS Compliance Statement

None of the following materials are intentionally added in manufacturing this product: lead, mercury, cadmium, hexavalent chromium, polybrominated biphenyls (PBB) or polybrominated diphenyl ethers (PBDE) as outlined in the Directive 2002/95/EC Article 4.1. See Protektive Pak Inc. letter on-line at ProtektivePak.com.

TRANSPARENT STATIC DISSIPATIVE (PINK POLY)

PROTEKTIVE PAK

PROTEKTIVE PAK
 13520 MONTE VISTA AVENUE, CHINO, CA 91710
 PHONE (909) 627-2578, FAX (909) 363-7331
ProtektivePak.com

DRAWING NUMBER
 49100

DATE:
 5/06